



Ruc. 2557942-1-827268 DV 8



Technical Specifications of Labelstock 09/DEC/2025

Product Code	Polieti Clear 80AC62					
Product Name	Fenix Clear Polyethylene 80 AC WG 62					
Face Stock	80μm High-quality Transparent PE					
Adhesive	Permanent Clear Adhesive					
Liner	62gsm White Glassine					
Items		Unit	Test Method			
Face Stock						
Caliper	80±5%	um	GB/T 451.3-2003			
Haze	20±5	%	GB/T 2410-2008			
Product surface using corona treatment, has excellent flexibility and tensile properties, and the processability is better. Mainly applicable to a certain anti-moisture and anti-extrusion requirements of the cosmetics and daily cosmetic products label.						
Adhesive						
'Loop' Tack	≥8	N	FTM9, ss			
Peel Adhesion (90°)	≥5	N/25mm	FTM2, ss			
Minimum Application Temp.	-5°C					
Service Temperature Range	-20°C~+100°C					
This product uses permanent clear acrylic adhesive, it has excellent performance in many packaging materials. Has a good die cutting and waste discharge performance.						
Liner						
Basic Weight	62±5%	g/m ²	GB/T 451.2-2002			
Caliper	60±5%	μm	GB/T 451.3-2003			
Tensile Strength (MD)	≥6.0	kN/m	GB/T 12914-1991			
Printing and Converting						
The specially treated surface can be used for letterpress, flexo, gravure and screen printing methods. Suitable for UV inks and water-based inks. Avoid overheating leading to material deformation in the processing. In order to ensure the best ink wettability and firmness during printing, it is recommended to use on-line corona treatment and use PE film-specific inks. Ink testing is always recommended before production. In order to ensure smooth processing, it is recommended to use a sharp film-specific die cutter, especially in the flat die cutting method. Bronzing performance and result are better. To avoid adhesive oozing from the label edge, tension should be controlled during rewinding. The material can be used in food if and only if it has a barrier, it is not suitable for direct contact with food						
Storage and Preservation						
One year when stored at 23±2°C and 50±5% RH. If test qualified, the label can continually be used after shelf life.						

Note:

1. All relative material's description, technical specification and usage recommendation are based upon tests believed to be reliable but do not represent a guarantee.
2. Is mandatory test before production to avoid potential risks, due to various operating environments and processing conditions.
3. All information and recommendations about Fenix® products are based on our existing knowledge and experiences but do not mean a guarantee or warranty. As the products are used for different applications we recommend checking suitability of products prior to use. All information is subject to change without notice. End user obliged and verifies the above information before using the material.
4. A.S.I Development Inc. Reserves the right to interpret latest terms to the technical documents.

Address: Galera Hermanos Acosta Loreto, Miraflores Street, beside Herreria D/L León, La Mitra sector, Corregimiento of Playa Leona, La Chorrera District, Panama West Province, Panama Republic. ZIP 07079. Phone: +507 3431240/1241. asidevelopmentinc@gmail.com